

1. PRODUCT NAME

ProSpec® Cure & Seal WB 1315

2. MANUFACTURER

Bluestone Products™, a TCC Materials® company
2025 Centre Pointe Blvd, Suite 300
Mendota Heights, MN 55120 USA

Phone: 1.651.688.9116
Fax: 1.651.688.9164
Internet: tccmaterials.com

3. PRODUCT DESCRIPTION

ProSpec® Cure & Seal WB 1315 is a film-forming compound that meets ASTM C1315 performance standards for water loss when applied properly to cure, seal, and harden freshly placed concrete, terrazzo, brick, stone, architectural concrete, and other cementitious materials. Cure & Seal WB 1315 will pass all VOC compliance laws and is formulated to cure, seal, protect, and dustproof concrete, as well as seal many types of porous tile and resilient floors. Designed for both exterior and interior applications, it is particularly recommended for indoor work in public buildings (hospitals, restaurants) and private residences where solvent-based systems are difficult to use. The white solution dries clear and provides a dust-free surface. This product provides maximum hardness to the concrete as well as resistance to traffic abrasion. Construction debris are easier to clean. Compatible with most tile and carpet adhesives.

Features and Benefits

- Meets ASTM C1315 type 1
- Low VOC, water-based mix
- Tack-free in 2–4 hours
- Ready to use (no diluting)
- Chemical resistant
- Sprays white, dries clear

Uses

- Cure and seal surfaces
- Interior or exterior applications
- New or existing applications
- Concrete, masonry, terrazzo, brick, stone, masonry, and other cementitious materials.
- Decorative concrete
- Odor-sensitive locations
- Commercial and residential applications

SAFETY

READ THE SAFETY DATA SHEET (SDS) BEFORE USING THIS PRODUCT. SDS information is available on our website: tccmaterials.com or contact TCC Materials® at 651–688–9116 (7:30 AM to 4:00 PM Central US Time).

CAUTIONS

Read complete cautionary information printed on product container prior to use.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered ProSpec® brand product(s) under normal environmental and working conditions. Because each project is different, neither ProSpec® nor TCC Materials® can be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

NOTE: These dry times are dependent on normal drying

Typical Results of ProSpec® Cure & Seal WB 1315	
Composition and Materials	Formulated of fine quality, hard, but pliable acrylic polymers in an aqueous system. No fillers are used and there are no oils, waxes or saponifiable resins. ProSpec® products are manufactured with only the finest quality raw materials available and close quality-control is practiced.
Moisture Efficiency	0.38kg/m2 at 300 sq. ft./gal
Typical Drying Time @ 70°F	1–2 hours (touch) 4–12 hours (traffic)
VOC Content	< 200 g/l
A.I.M. Category	Concrete Curing Compound Maximum VOC 350 g/l
Applicable Standards	ASTM C 1315 Type 1, Class A, B, and C, ASTM C–309, Type 1, Class A, B and Type 1D with a red dye added. Fed. TT–C–800A, Type 1, Class 1 ACI Standard 302.77 for use on Class 1, 2, 3, and 4 concrete floors AASHTO Des. M–148, Type 1, Clear USDA Authorization for use in meat, poultry, and food processing plants. Resilient Tile Institute approval for compatibility with most resilient tile, carpet adhesives, and paints.

conditions. Cool temperatures or high humidity will slow the drying time.

Packaging

- 1 gal. bottle (3.78 L) – Product #129910
- 5 gal. pail (18.93 L) – Product #129920
- 55 gal. drum (208 L) – Product #129930

Shelf Life

For best use, the recommended shelf life is 12 months. If age is beyond 12 months, please contact your distributor. Store in the original, tightly closed container, out of direct sunlight. Protect from freezing, store at 50°F–90°F (10°C–32°C).

5. INSTALLATION

Preparation: Existing Concrete

- Remove all loose or unsound materials prior to application.
- Thoroughly clean existing surfaces of dirt, dust, oil, grease or other contaminants before using. TSP (Trisodium Phosphate) in very hot water can be used, rinse well and allow to dry.
- Check compatibility with the substrate manufacturer prior to placement.
- Do not apply when rain is expected within 4–6 hours of application.

Preparation: Freshly Placed Concrete

- Ensure surfaced bleed water has evaporated prior to applying.
- Surface must be hard enough as not to mark during material application.

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

Job Mockups

The manufacturer requires that when its ProSpec® products are used in any application or as part of any system that includes other manufacturers' products, the contractor and/or design professional shall test all the system components collectively for compatibility, performance and long-term intended use in accordance with pertinent and accepted industry standards prior to any construction. Written documentation of the tests performed shall be satisfactory to the design professional and contractor. Test results must include the means and methods of application, products used, project-specific conditions being addressed, and standardized tests performed for each proposed system or variation.

Mixing

- Mixture may be gently stirred to blend prior to use.
- Do not dilute.

Application

New Concrete: Curing

Apply after troweling is complete and surface is dry, immediately after surface water has dissipated and concrete can withstand weight. Use of a low-pressure sprayer is best to apply uniformly at the specified rate of coverage, however other

application methods can be used i.e. lamb's wool applicator, or medium nap roller.

Existing Concrete: Sealing

Apply to a clean, dry surface. Use a medium nap roller or low-pressure sprayer to apply uniformly, avoiding heavy accumulations. A second coat may be applied on very porous surfaces with rapid absorption. Allow the product to become tack-free between coats. Spray the second coat with good pressure and a mist of spray from the nozzle.

1. Apply only when air and substrate temperatures are between 50°F–90°F (10°C–32°C). Apply to dry surfaces only for optimal performance
2. Use low-pressure sprayer to apply uniformly at the specified rate of coverage. Avoid heavy accumulation. A lamb's wool applicator or medium nap roller can also be used.
3. Do not allow exposure to rainfall, water, or traffic until fully dried.

Note: Cure & Seal WB 1315 may darken the appearance of concrete, especially if it is applied too heavily. A small mock-up in an inconspicuous area is often done to test compatibility with the substrate prior to full application.

Cleaning

Use warm water and soap before this material dries. After product dries, an organic solvent such as xylene, may be used.

Limitations

- Store and apply between 50°F–90°F (10°C–32°C). Do not allow product in container to freeze.
- Avoid build-up or over-application of product as this may cause slippery conditions or separation between coats.
- Keep containers tightly sealed when not in use.
- Wash hands after using.
- Do not dilute with water or solvents.
- Dispose of contents/container in accordance with all local and state regulations.
- May highlight imperfections in concrete surface.
- Extended exposure to water before full cure may cause whitening.
- Sealing and dust proofing require a second coat
- Keep out of reach of children.

Coverage

Note: Coverage is per coating and may vary due to porosity, wind, temperatures, and condition of surfaces.

6. AVAILABILITY

To locate ProSpec® products in your area, please contact:

Phone: 1.651.688.9116
Email: info@tccmaterials.com

Approximate Coverage @ 70°F (21°C)	Sq. Ft./Gal.	M ² /L
Curing: Broomed or Troweled	200–300	4.9–7.3
Second Coat	300–500	7.3–12.6

7. WARRANTY

Seller warrants that its product will conform to and perform in accordance with the product specifications. The foregoing warranty is in lieu of all other warranties, expressed or implied, including, but not limited to those concerning merchantability and fitness for a particular purpose. Because of the difficulty in ascertaining and measuring damages hereunder, it is agreed that Seller's liability to the Buyer shall not exceed the total amount billed and billable to the Buyer for the product hereunder.

8. MAINTENANCE

Not applicable.

9. TECHNICAL SERVICES

Technical Assistance:

Information is available by calling TCC Materials® (hours 7:30 AM to 4:00 PM CST):

Phone: 1.651.688.9116
 Fax: 1.651.688.6164
 Web: tccmaterials.com

Technical and Safety Literature:

To acquire technical and safety literature, please visit our website at: tccmaterials.com.

10. FILING SYSTEM

Division 9

©Copyright 2020 TCC Materials®

Data Sheets are subject to change without notice. For the latest revision, check our website at tccmaterials.com



2025 Centre Pointe Blvd, Suite 300,
 Mendota Heights, MN 55120

REV 09/20

TDS.PS.129910