






ADVANTAGES/USES	100% SILANE SEALER	40% SILANE SEALER	20% SILANE SEALER	CURE & HARDEN
	 <ul style="list-style-type: none"> • Protects and seals • 100% active content • High chloride ion resistance • Early water repellency • Breathable and deeply penetrating • Natural looking, invisible protection • Non-staining, colorless, non-yellowing • Ready to use 	 <ul style="list-style-type: none"> • Protects and seals • 40% active content • High chloride ion resistance • Early water repellency • Breathable and deeply penetrating • Natural looking, invisible protection • Non-staining, colorless, non-yellowing • Ready to use • Solvent based 	 <ul style="list-style-type: none"> • Protects and seals • 20% active content • High chloride ion resistance • Early water repellency • Breathable and deeply penetrating • Natural looking, invisible protection • Non-staining, colorless, non-yellowing • Ready to use • Solvent based 	<p style="text-align: center;">COMING SOON</p> <ul style="list-style-type: none"> • Sodium silicate • Hardens concrete surfaces • Improves abrasion resistance • Extends concrete service life • Aids in curing of newly finished concrete • Minimizes shrinkage cracking • Non-staining, non-yellowing • Ready to use • Water based, 0g/L VOC • Will not inhibit adhesion of secondary coatings or adhesives
APPLICATION				
Temperature Range	Best above 40°F	Best above 40°F	Best above 40°F	Best above 50°F
VOC	< 350 g/L	< 600 g/L	< 600 g/L	< 0 g/L
Typical Drying Time @ 70°F	1-2 hour (touch) 2-4 hours (traffic)	1-2 hour (touch) 2-4 hours (traffic)	1-2 hour (touch) 2-4 hours (traffic)	1-2 hours
Product Classification	Sealing	Sealing	Sealing	Hardener/Densifier
Dosage Rate	40-250 SF/Gal	40-250 SF/Gal	40-250 SF/Gal	200-500 SF/Gal
Intended use	Sealing fully cured concrete & multiple surfaces	Sealing fully cured concrete & multiple surfaces	Sealing fully cured concrete & multiple surfaces	Densify surface of new & existing concrete



ADVANTAGES/USES	HARDENER LS	ULTIMATE BARRIER	CURE & SEAL WB 1315	CURE & SEAL ES
	COMING SOON	COMING SOON		COMING SOON
	<ul style="list-style-type: none"> • Lithium silicate • Hardens concrete surfaces • Improves abrasion resistance • Extends concrete service life • Deep penetrating permeant chemical reaction • Non-staining, non-yellowing • Ready to use • Water Based, 0g/L VOC • Will not inhibit adhesion of secondary coatings or adhesives 	<ul style="list-style-type: none"> • One-step curing and sealing • ASTM C1315 and ASTM C309 compliant • 25% solids • Chloride ion resistance • Early water repellency • Ready to use (no diluting) • Dries tack free • High alkali resistance • Easy to apply with sprayer and roller • Protects from effects of rain and other water penetration, chemicals, salt freeze-thaw, and smog 	<ul style="list-style-type: none"> • Water based • VOC content compliant in OTC & LADCO regulated states and Canada • ASTM C1315 and ASTM C309 compliant • 30% solids • Protects and seals surface from dirt and damage • Enhances appearance • Sprays white, dries clear 	<ul style="list-style-type: none"> • Solvent based • VOC content compliant in OTC & LADCO regulated states and Canada • ASTM C1315 and ASTM C309 compliant • 25% solids • Protects and seals surface from dirt and damage • Enhances appearance • Ready to use (no diluting) • Sprays clear, dries clear
APPLICATION				
Temperature Range	Best above 50°F	Best above 40°F	Best above 50°F	Best above 40°F
VOC	0 g/L	< 700 g/L	150 g/L	< 350 g/L
Typical Drying Time @ 70°F	1-2 hours	1 hour (touch) 2 hours (traffic)	1-2 hours (touch) 4-12 hours (traffic)	1-2 hours (touch) 2-4 hours (traffic)
Product Classification	Hardener/densifier	Curing & sealing compound	Curing & sealing compound	Curing & sealing compound
Dosage Rate	250-800 sq.ft./gal	300-500 sq. ft./gal	300-500 sq. ft./gal	300-500 sq. ft./gal
Intended use	Densify surface of new and existing concrete	Curing new concrete; sealing existing concrete & multiple surfaces	Curing new concrete; sealing existing concrete & multiple surfaces	Curing new concrete; sealing existing concrete & multiple surfaces