



1. PRODUCT NAME

Tenon® Dissipating Cure WB +PLUS

2. MANUFACTURER

TCC Materials®
2025 Centre Pointe Blvd.
Mendota Heights, MN 55120 USA

Phone: 1.651.688.9116
Fax: 1.651.688.9164
Internet: tccmaterials.com

3. PRODUCT DESCRIPTION

Tenon® Dissipating Cure WB +PLUS is a water-based, clear resin, liquid membrane forming, curing compound with silane used for moisture retention of freshly placed concrete. Tenon® Dissipating Cure WB +PLUS is formulated for curing concrete. Designed for interior or exterior applications where a dissipating or easily removed curing compound is required. It is particularly recommended for applications where greater moisture retention is required. Tenon® Dissipating Cure WB +PLUS will pass all VOC compliance laws.

Features and Benefits

- VOC Compliant
- Tack-free in 2–4 hours (cooler or more humid conditions will extend drying time)
- Ready to use (no diluting)
- Dissipating Resin Cure
- Silane enhanced to provide greater weather protection
- Clean-up with water (after dry, a tool cleaning solvent may be required)
- Easily removed via exposure to ultra violet sunlight, weathering, traffic, or pressure washer (interior applications)

Uses

- Cure concrete surfaces
- Exterior or interior applications
- New applications once bleed water has disappeared.
- Industrial, Commercial, and Residential applications

SAFETY

READ THE SAFETY DATA SHEET (SDS) BEFORE USING THIS PRODUCT. SDS information is available on our website: tccmaterials.com or contact TCC Materials® at 651-688-9116 (7:30 AM to 4:00 PM Central US Time).

CAUTIONS

Read complete cautionary information printed on product container prior to use.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered Tenon® brand product(s) under normal environmental and working conditions. Because each project is different, neither Tenon® nor TCC Materials® can be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

- Complaint with Federal US EPA VOC regulations for Concrete Curing Compounds. Meets requirements of U.S. EPA, LADCO, SCAQMD, and OTC.
- NOTE: These dry times are dependent on normal drying conditions. Cool temperatures or high humidity will slow the drying time.

Composition and Materials	Formulated with a refined petroleum wax to form a watertight membrane to protect the substrate from heat build-up. Tenon® products are manufactured only with the finest quality raw materials available and close quality-control is practiced.
Moisture Efficiency	Meets ASTM C-1315 Type 1 Class C maximum allowed 0.40 kg/m2
Typical Drying Time @70°F	1–2 hours (touch) 4–12 hours (traffic)
Active Solids	18%
Cured Solids	16%
VOC Content	<350 g/L
A.I.M. Category	Concrete Curing Compound maximum VOC 350 g/L

Packaging

- 1 gal. bottle (3.78 L) – #114437
- 5 gal. pail (18.93 L) – #114447
- 55 gal. drum (208 L) – #114457
- 275 gal. tote (1041 L) – #114467

Shelf Life

For best use, the recommended shelf life is 12 months. If shelf life is beyond 12 months, please contact your distributor. Store in the original labeled container, away from moisture, out of direct sunlight. Keep containers tightly sealed when not in use.

5. INSTALLATION

Preparation

- Read all directions before starting work. Read and understand SDS pages for safety precautions prior to use.
- Check compatibility with the substrate manufacturer prior to placement.
- Do not apply when rain is expected within 4–6 hours of application.

Note: It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

Job Mockups

The manufacturer requires that when its Tenon® products are used in any application or as part of any system that includes other manufacturers' products, the contractor and/or design professional shall test all the system components collectively for compatibility, performance and long-term intended use in accordance with pertinent and accepted industry standards prior to any construction. Written documentation of the tests performed shall be satisfactory to the design professional and contractor. Test results must include the means and methods of application, products used, project-specific conditions being addressed, and standardized tests performed for each proposed system or variation.

Mixing

- Mixture should be gently stirred to blend prior to use.
- Do not over agitate or use high speed mixing equipment.
- Do not dilute.

Application

New Concrete: Curing

Apply after troweling is complete and surface is dry, immediately after surface water has dissipated and concrete can withstand weight.

- Apply only when air and substrate temperatures are between 50°F–90°F (10°C–32°C). Apply to dry surfaces only for optimal performance.
- Use a low-pressure sprayer to apply uniformly at the specified rate of coverage. Avoid heavy accumulation. A lamb's wool applicator or medium nap roller can also be used.
- Do not allow exposure to rainfall, water, or traffic until fully dried.

Note: Tenon® Dissipating Cure WB +PLUS may darken/yellow the appearance of concrete, especially if it is applied too heavily. A small mock-up in an inconspicuous area is often done to test compatibility with the substrate prior to full application.

Cleaning

Use warm water and soap before the product dries. After product dries an organic solvent such as Tenon® Xylene, may be used.

Limitations

FOR PROFESSIONAL USE ONLY! Store and apply between 50°F–90°F (10°C–32°C). Do not allow product in container to freeze. Do not apply below 40°F (4°C). Avoid build-up or over-application of product as this may cause slippery conditions, separation between coats, and/or surface yellowing. For vertical applications, apply two light coats. Tenon® Dissipating Cure WB +PLUS will chemically break down in 5 to 8 weeks when exposed to ultraviolet light/sunlight. Areas not exposed to sunlight will require surfaced to be cleaned with a hot water power washer. If substrate surface is to receive a coating, adhesive, or floor topping, all residual cure must be removed. Keep containers tightly sealed when not in use. Wash hands after using. Do not dilute with water or solvents. Dispose of contents/containers in accordance with all local and state regulations. Keep out of reach of children.

Coverage Rate

Note: Texture and absorption of forming material will dictate final coverage rate.

6. AVAILABILITY

To locate Tenon® products in your area, please contact:

Phone: 1.651.688.9116
Email: info@tccmaterials.com

7. WARRANTY

Seller warrants that its product will conform to and perform in accordance with the product specifications. The foregoing warranty is in lieu of all other warranties, expressed or implied, including, but not limited to those concerning merchantability and fitness for a particular purpose. Because of the difficulty in ascertaining and measuring damages hereunder, it is agreed that Seller's liability to the Buyer shall not exceed the total amount billed and billable to the Buyer for the product

Approximate Coverage @ 70°F (21°C)	Sq. Ft. / gal	Sq. M. / L
Curing: Broomed Finish	200-300	4.9-7.3
Steel/Power Troweled Finish	300-500	7.9-12.6

hereunder.

8. TECHNICAL SERVICES

Technical Assistance:
Information is available by calling TCC Materials®
(hours 7:30 AM to 4:00 PM CST):

Phone: 1.651.688.9116
Email: info@tccmaterials.com
Web: tccmaterials.com

Technical and Safety Literature:
To acquire technical and safety literature, please visit our
website at: tccmaterials.com.

9. FILING SYSTEM

Division 3

©Copyright 2020 TCC Materials®

Data Sheets are subject to change without notice. For the latest
revision, check our website at tccmaterials.com



2025 Centre Pointe Blvd.
Mendota Heights, MN 55120