



TENON[®]

Burnished Block Sealer WB



Enhances color & adds sheen

Tenon[®] Burnished Block Sealer WB protects and enhances masonry surfaces like burnish block, brick, slate, and tile with a durable, UV-resistant acrylic finish. It creates a breathable, wet-look membrane that resists freeze-thaw damage, salts, chemicals, oils, and dirt—keeping surfaces cleaner and more vibrant over time.

Features:

- Non-staining, non-yellowing
Ready to use (no diluting)
- Makes surfaces less dusty and easier to clean by resisting penetration of grease or rust stains on concrete surfaces
- Easy to apply with sprayer, roller, or long nap applicator
- Protects from effects of rain water penetration, chemicals, oils, salt, freeze-thaw, smog, and contaminants
- 2-hour drying time under normal conditions
- Wear patterns can be easily re-coated



Application

- Apply only to surfaces when air and substrate temperatures are between 40°F-100°F (4°C-38°C) and the Burnished Block Sealer is above 50°F (10°C). For best results, avoid application in direct sunlight.
- Apply with an airless sprayer, roller, or with a long napped applicator at the rate of 300-500 sq. ft. per gal.
- Sprayers must be equipped with neoprene or other compatible fittings as the solvent can damage rubber fittings.
- Work the Burnished Block Sealer WB into the surface, avoiding pools, runs, sags, or the creation of lap marks. Do not over apply
- Surface should have a uniform coating.
- May also be used on fully cured, dry, horizontal surfaces using a low-pressure sprayer, roller, or brush.

Approximate Coverage @ 70°F (21°C)	Sq. Ft. / Gal.	M ² / L
Burnished Block	250 - 500	6.1 - 12.3
Horizontal Surfaces	250 - 500	6.1 - 12.3

Available In:

Tenon[®] Burnished Block Sealer WB is available in 1 gal. bottle, 5 gal. pail, and 55 gal. drum.



55 Gal
BOM #121113



5 Gal
BOM #121107



1 Gal
BOM #121110

For professional use only.

It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use. For technical assistance, please contact TCC Materials. To acquire technical and safety literature, please visit our website.